

Standart waxes						
Product	Melting point (°C)	Oil content (%)	Penetration	Colour	Shape	
Paraffin G3	57-60	0.7-1%	13-20	white	Slabs	
Paraffin G2	55-57	0.7-1%	13-20	white	Slabs	
Paraffin G3L	57-60	1.5%max	30 max	white	Slabs	
Paraffin G3E	63-69	3% max	20-30	white	Slabs	
Paraffin G5	50-60	15 max	50 max	white	Slabs	
Paraffin London	50-54	4-7%	25-35	yellowish	Slabs	
Paraffin M4	62-66	1.5 %max	15-24	white	Slabs	
Paraffin M5	52-54	0.5%max	25 max	white	Slabs	
Paraffin M6	56-58	0.5% max	20 max	white	Slabs	

Paraffin Cyclon	56	0.8%	8	yellowish	Slabs	
Paraffin M7	54-56	0.5% max	20 max	white	Slabs	
Paraffin M8	57-59	0.75%max	12-17	white	Slabs	
Paraffin M9	58-60	0.5%max	20 max	white	Slabs	
Paraffin M10	60-62	0.5%max	20 max	white	Slabs	
Paraffin M11	70-75	2% max	12-20	yellowish	Slabs	
Paraffin M12	58.5-60.5		10-14	White	Slabs	
Paraffin C5860	58-60	0.5%	19	White	Slabs	
Paraffin C5860F	58-60	0.5%	15	White	Slabs	
Paraffin C5860S	58-60	1.5%	20	White	Slabs	
Granulated Paraffin C1	57-60	0.7-1%	13-20	white	Powder	
Granulated Paraffin F1	50-54	1-1.5%	28-30	white	Powder	

Granulated Paraffin S1	56-62		28-43	White	Powder	
Granulated Paraffin H1	57-60	0.7-1%	13-20	White	Granules	

Stearic acid						
Product	Melting point (°C)	Acid value	Iodine value	Colour	Shape	
Stearic acid F1	58-60	201-205	Max 0.5	White	flakes	
Stearic acid C1	54-57	207-212	Max 0.5	White	flakes	